

MINING QUICK REFERENCE GUIDE

MINING EXTREME CORROSION										
COATING SYSTEM	DESCRIPTION	PAINT SYSTEM	DFT (MILS)	V.O.C'S	UV RESISTANCE	CORROSION	ABRASION	IMPACT	CHEMICAL RESISTANCE	OVERALL
MINING EXTREME CORROSION	ZINC RICH EPOXY PRIMER	EF75250	2-3	<3.5	N/A	3000+ HRS				
	EPOXY INTERMEDIATE COAT	EF72000 OR EF75000	2-3	>3.5 <3.5	N/A					
	TOPCOAT	839 SERIES ARMOURSHIELD	2-4	<3.5	5		5	2	5	4

MINING LIGHT-MED CORROSION										
COATING SYSTEM	DESCRIPTION	PAINT SYSTEM	DFT (MILS)	V.O.C'S	UV RESISTANCE	CORROSION	ABRASION	IMPACT	CHEMICAL RESISTANCE	OVERALL
MINING LIGHT - MED CORROSION	EPOXY PRIMER	EF75000	3-4	<3.5	N/A	1000+ HRS				
	TOPCOAT	839 SERIES ARMOURSHIELD	2-4	<3.5	5		5	3	5	4

All ratings are on a scale of 1-5 with 1 being the least and 5 the best.

MINING SPECIALTY COATINGS								
COATING SYSTEM	DESCRIPTION	PROPELLANT	GLOSS	V.O.C	SAG	SOLIDS	COLORS	SHELF LIFE
SPLATTER AEROSOLS	MINE MARKING COATING	NON FLAMMABLE	>80@60	3.92	10-20 MILS	40-44%	EB0226600AS YELLOW EB0462200AS RED	6 MONTHS